

UltraPur™ TEB11

¹¹B Enriched triethylborate

Triethylborate (TEB) is an organic boron ester compound which is widely used as a boron source in the deposition of doped silicate glass in a low-pressure and plasma-enhanced CVD. Boron and phosphorus act as glass flow temperature modifiers and gettering agents. The softening temperature of the silicate glass is modified with varying concentrations of doping constituents.

It has been reported that collisions of boron nuclei with neutrons resulting from cosmic radiation can produce alpha particles in boron containing films. The effective size of the nucleus of the ¹⁰B isotope makes it far more susceptible to this phenomenon than the ¹¹B isotope. By reducing the percent of ¹⁰B, the probability of an event occurring that will produce an alpha particle is reduced.

Triethylborate (TEB) synthesized from naturally occurring boron is comprised of approximately 19.9% ¹⁰B and 80.1% ¹¹B. The boron content of Entegris UltraPur™ TEB11 is less than 0.1% ¹⁰B or greater than 99.9% ¹¹B. This reduction of ¹⁰B content significantly reduces the probability of alpha particle producing collisions in films made with UltraPur TEB11.


The only difference between TEB and UltraPur TEB11 is the isotopic enrichment in TEB11, therefore, TEB11 can be introduced into existing processes without the requirement to change other process parameters.

Entegris UltraPur TEB11 is synthesized from isotopically enriched boron starting materials, purified, and packaged in our state-of-the-art manufacturing facility in Burnet, Texas.

Canisters and delivery systems

Entegris UltraPur TEB11 is available in a wide variety of stainless steel canisters and ampoules to fit all tools and delivery systems. Standard sizes include 2-, 5- and 10-gallon minibulk canisters which can be configured to fit a wide range of applications. Options include automatic valves and level sensors. Entegris UltraPur TEB11 is also available in patented Entegris high-efficiency 12-liter ampoules for use in Entegris chemical delivery systems.

Entegris offers the Unichem™ 3100 chemical delivery system for single chemical applications.



APPLICATIONS


- Plasma-enhanced CVD deposition

FEATURES & BENEFITS

- Lower probability of damage or soft errors due to alpha particles created in the films
- Improved performance characteristics over diborane
- Replaces diborane and trimethylborate
- Ease of handling a liquid source
- Reduced health hazards
- Improved purity levels
- Standard shelf life of 24 months

PERFORMANCE DATA

Vapor Pressure Curve



SPECIFICATIONS

Physical properties

Chemical formula	C ₆ H ₁₅ O ₃ B
Molecular weight	146.02
Density	0.858 gm/mL
Boiling point	118.5°C (245.3°F) @ 0.1 mm Hg
Melting point	-85°C (-121°F)
Flash point (closed cup)	11°C (51.8°F)

Purity analysis

Element	Specification	Analytical method
Aluminum	0.200 ppb	ICP-MS
Antimony	0.100 ppb	ICP-MS
Arsenic	0.100 ppb	ICP-MS
Barium	0.100 ppb	ICP-MS
Beryllium	0.100 ppb	ICP-MS
Bismuth	0.100 ppb	ICP-MS
Cadmium	0.050 ppb	ICP-MS
Calcium	0.800 ppb	ICP-MS
Cerium	0.050 ppb	ICP-MS
Chromium	0.100 ppb	ICP-MS
Cobalt	0.050 ppb	ICP-MS
Copper	0.100 ppb	ICP-MS

Purity analysis (continued)

Element	Specification	Analytical method
Gallium	0.050 ppb	ICP-MS
Germanium	0.050 ppb	ICP-MS
Gold	0.100 ppb	ICP-MS
Hafnium	0.050 ppb	ICP-MS
Indium	0.050 ppb	ICP-MS
Iridium	0.050 ppb	ICP-MS
Iron	0.300 ppb	ICP-MS
Lead	0.100 ppb	ICP-MS
Lithium	0.050 ppb	ICP-MS
Magnesium	0.200 ppb	ICP-MS
Manganese	0.100 ppb	ICP-MS
Mercury	0.100 ppb	ICP-MS
Molybdenum	0.100 ppb	ICP-MS
Nickel	0.200 ppb	ICP-MS
Niobium	0.050 ppb	ICP-MS
Palladium	0.050 ppb	ICP-MS
Platinum	0.050 ppb	ICP-MS
Potassium	0.200 ppb	ICP-MS
Rhenium	0.050 ppb	ICP-MS
Rhodium	0.050 ppb	ICP-MS
Rubidium	0.050 ppb	ICP-MS
Silver	0.050 ppb	ICP-MS
Sodium	0.500 ppb	ICP-MS
Strontium	0.050 ppb	ICP-MS
Tantalum	0.050 ppb	ICP-MS
Thallium	0.050 ppb	ICP-MS
Thorium	0.050 ppb	ICP-MS
Tin	0.100 ppb	ICP-MS
Titanium	0.100 ppb	ICP-MS
Tungsten	0.050 ppb	ICP-MS
Uranium	0.100 ppb	ICP-MS
Vanadium	0.500 ppb	ICP-MS
Zinc	0.200 ppb	ICP-MS
Zirconium	0.050 ppb	ICP-MS

Purity analysis (continued)

Parameter	Specification	Analytical method
Assay	99.99%	GC
Chloride	50 ppb	Typical
Color	5	Typical
Purity	99.9999995%	ICP-MS
Water	10 ppm	KF Titrator

Standard TEB11 fill weights for Entegris canisters

5-gallon	15,750 grams
10-gallon	31,500 grams

FOR MORE INFORMATION

Please call your Regional Customer Service Center today to learn what Entegris can do for you. Visit entegris.com and select the Contact Us link to find the customer service center nearest you.

TERMS AND CONDITIONS OF SALE

All purchases are subject to Entegris' Terms and Conditions of Sale. To view and print this information, visit entegris.com and select the Terms & Conditions link in the footer.



Corporate Headquarters
129 Concord Road
Billerica, MA 01821
USA

Customer Service
Tel +1 952 556 4181
Fax +1 952 556 8022
Toll Free 800 394 4083

Entegris®, the Entegris Rings Design™, Pure Advantage™, UltraPur™ and Unichem™ are trademarks of Entegris, Inc.
©2016-2017 Entegris, Inc. | All rights reserved. | Printed in the USA | 7400-8040ENT-0917