



## ULTRAC™-HT COATING

*Exceptionally tough diamond-like carbon*

### Overview

Entegris uses its proprietary low-temperature plasma enhanced chemical vapor deposition process to deposit UltraC™-HT coatings. UltraC-HT is an innovative, multilayer, fully dense coating based on our UltraC Diamond hard carbon coating technology. This mono-dimensionally modulated (MDM) coating system, is engineered to consist of multiple layers of two different materials with different elastic modulus. The UltraC-HT coatings have high strength, toughness and excellent resistance to erosion and wear. UltraC-HT coatings are suitable for a wide range of demanding applications in aggressive environments encompassing semiconductor wafer processing, oil exploration, biomedical engineering and aerospace.

### Applications

- Semiconductor wafer handling devices
- Oil exploration equipment
- Aerospace turbine compressor blades
- Air bearings
- Surgical tools
- Metal forming

### Features

- Multilayer coatings provide high strength and extreme toughness
- Maintains lubrication in both dry and humid air
- Excellent abrasive/erosion wear resistance
- Super lubricious



*Stainless steel component coated with UltraC-HT coating.*



*Rotating vacuum seal surfaces on an aluminum component coated with UltraC-HT coating.*

## Specifications

Substrate:	Compatibility	Most metals and ceramics (AlN, Al <sub>2</sub> O <sub>3</sub> , quartz, YSZ, silicon, graphite, etc.), silicon wafers and polymers
	Size	Up to 91 cm (36")
	Geometry	Any shape, including complex geometries
Structure:	Dense, amorphous, mono-dimensionally modulated (MDM), multilayered	
Temperature:	Deposition	150°C (302°F)
	Use	-50 to 400°C (-58 to 752°F)
Coating thickness:	1–50 µm	
Electrical resistivity:	~10 <sup>8</sup> Ω-cm	
Coefficient of friction:	0.04–0.08	
Hardness:	2040–2650 HV (20–26 GPa)	
Wear resistance:	Excellent	
Corrosion resistance:	Resistant to most acids and alkalis, acid fluxes and solders	

## For More Information

To learn more about how Entegris' high-purity specialty coatings help customers enhance yields, improve productivity and meet future technological needs, call Entegris at +33 (0)4 72 52 00 40.

To review Entegris' specialty coatings offering, visit Entegris' website at [www.EntegrisSpecialtyCoatings.com](http://www.EntegrisSpecialtyCoatings.com).

## Terms and Conditions of Sale

All purchases are subject to Entegris' Terms and Conditions of Sale. To view and print this information, visit [www.entegris.com](http://www.entegris.com) and select the Legal Notices link from the footer.

Entegris®, the Entegris Rings Design®, Creating a Material Advantage® and UltraC™ are trademarks of Entegris, Inc.

### ENTEGRIS, INC.

Corporate Headquarters | 129 Concord Road | Billerica, MA 01821 USA  
Customer Service Tel. +1 952 556 4181 | Customer Service Fax +1 952 556 8022  
In North America 800 394 4083 | [www.entegris.com](http://www.entegris.com)